

CYTOTOXICITY TEST

REPORT N. 7804-20 Rev. 00

Customer: **AT Dental & Textile S.r.l. Start Up**
Via Giovanni Battista Tiepolo, 36 - 00196 ROMA

TEST METHOD ISO 10993-12:2012 + ISO 10993-5:2009 Annex A

TIME SCHEDULE

Acceptance N.:	20-7385
Reception date:	05/11/2020
Start test date:	09/11/2020
End test date:	11/11/2020
Operator:	Dr. E. Fabbri

TEST SAMPLE IDENTIFICATION

Name:	not provided
Sample Typology:	Mascherine Chirurgiche
Composition:	Polipropilene Spunbond-Meltblown-Spunbond
Quantity tested:	1
Code (REF):	not provided
LOT:	10102020
Manufacturing date:	15/10/2020
Expiry date:	15/01/2021
Sterilization Method:	Ultravioletto
Sterilization lot:	n/a
Sterilization Date:	15/10/2020
Sterilization Unit:	n/a

The information concerning the test sample were provided by the Customer. All data related to the test sample are under the responsibility of the Customer and have not been verified by the test laboratory.

Issue Date	Rev.	Change Description	Prepared by: Dr. E. Fabbri (Laboratory Technician)	Verified and Approved by: Dr. Renzo Giovanni Coronati (Managing Director Laboratory)
16/11/2020	00	First Issue	<i>Elisa Fabbri</i>	<i>Renzo Coronati</i>

This test report is digitally signed by Dr. Renzo Giovanni Coronati.
The digital signature has legal value according to Italian D. Lgs. 82/2005 and subsequent amendments.

*The sampling is performed by the Customer. The test results relate only to the test sample.
This report shall not be reproduced except in full without the written approval of Coronati Consulting srl.*

TEST LABORATORY: **Coronati Consulting srl** Via L. Gavioli, 3 I-41037 Mirandola (MO) Italy Tel.+39 0535611533 Fax +390535410441
E-mail: info@coronaticonsulting.it Web: www.coronaticonsulting.it

PROCEDURES

All procedures used during this study are recorded in the Laboratory Coronati Consulting s.r.l.

OPERATING METHOD – (test on extracts)

Test Sample preparation

Under laminar flow hood in aseptic conditions, the device (without elastic bands) was put in contact with extracting solution (DMEM +NBCS). The quantity of extracting solution was selected according to the ratio of 0.1 g/ml (sample/extracting solution) required by the standard UNI EN ISO 10993-12. The sample has been maintained in contact with the extract solution at $37 \pm 1^\circ\text{C}$ for 24 hours and continuously stirred.

Negative control preparation

The extract of the negative control was prepared by immersing HDPE in culture medium, in order to reach a surface/volume ratio of $3 \text{ cm}^2/\text{ml}$. Then the test sample was incubated for 24 hours at temperature of $37 \pm 1^\circ\text{C}$

Positive control preparation

The extract of the positive control was prepared by immersing latex in culture medium, in order to reach a surface/volume ratio of $6 \text{ cm}^2/\text{ml}$. Then the test sample was incubated for 24 hours at temperature of $37 \pm 1^\circ\text{C}$.

Treatment

The test has been carried out using the cellular line BALB 3T3 clone A31 (fibroblasts from mouse embryo) that has a high capacity to proliferate (as recommended in UNI EN ISO 10993-5). Cell cultures were grown until a confluent monolayer in multiwell dishes. Sample extract in 6 replicates has replaced the medium in dishes containing cell cultures and it was incubated at $37 \pm 1^\circ\text{C}$ for 24 hours in at 10% CO_2 atmosphere. Negative control and positive control were prepared at the same time and submitted to the same process of the sample. At the end of incubation the cells were treated for 3 hours with a solution containing Neutral Red and by photometer the colouring intensity (proportional to cellular vitality) was measured.

REFERENCE CONTROLS

- HDPE – High Density PolyEthylene (Negative Control) (USP)
- Latex from glove (Positive Control) (VWR International S.r.l)

INSTRUMENTS AND EQUIPMENT

- Laminar flow hood (ATR 034)
- Stirrer with thermostatic cupola (ATR 066)
- CO_2 Incubator for cultures cell (ATR 156)
- Inverted Microscope (ATR 032)
- Photometer Microplate Reader (ATR 193)

ACCEPTANCE CRITERIA

- Mean of OD_{540} of negative control replicates must be $\geq 0,3$ ⁽¹⁾.
- Vitality of positive control must be $\leq 50\%$ ⁽¹⁾.
- C.V.% between replicates must be $\leq 20\%$.

⁽¹⁾ according to UNI EN ISO 10993-5:2009

INTERPRETATION OF RESULTS

- Sample is considered non cytotoxic if cellular vitality is $\geq 70\%$.
- Sample is considered cytotoxic if the cellular vitality is $< 70\%$.

RESULTS

Id.	Mean of OD_{540} of Negative Control replicates	$\geq 0,3$	Uncertainty estimated with factor K=2 (95%)	C.V.%
Sample Extract	86,5		$\pm 4,2$	10,5
Negative Control	100,0		$\pm 4,8$	5,2
Positive Control	10,8		$\pm 1,2$	5,6

CONFORMITY EVALUATION

Under the assay conditions the extract of the sample is considered NON-CYTOTOXIC.

DEVIATION

No deviation has been remarked during the study.

-----End of Report-----